

DEVELOPMENT OF OIL SHALE RETORTING PLANT IN JAPAN

PART II : OPERATION OF THE PILOT PLANT

TAKASHI YABUSHITA, KOICHI YUTA and TERUO OKI

Japan Oil Shale Engineering Co., Ltd.

10-3, Nishishinbashi 1-chome, Minato-ku, Tokyo 105, Japan

ABSTRACT

On consignment from the Ministry of International Trade and Industry (MITI) and the Japan National Oil Corporation (JNOC), Japan Oil Shale Engineering Co., Ltd. (JOSECO) commenced the operation of an oil shale pilot plant in May 1987.

Though JOSECO is still continuing the experimental operation as of the end of January 1988, all the data we have obtained to date have been satisfactory.

INTRODUCTION

After the integrated load trial runs and final adjustments of the pilot plant and the on-the-job training of the operators, the pilot plant started its formal operation in early May, 1987.

By the end of September preliminary tests were conducted. Through these preliminary tests, a number of factors have been checked and reviewed, including the performance and reliability of the equipment, procedures to ensure operational safety, and research on process conditions to maintain stable and efficient operations.

Based on the achievements of preliminary tests, JOSECO has been conducted the main tests using both Australian Condor and Chinese

Maoming ores. To date all the data we have obtained have been satisfactory.

This paper introduces the outline of pilot plant operation.

OPERATION SCHEDULE

Fig. 1 shows the operation schedule of the pilot plant after preliminary tests.

Fig. 1 Operation schedule

		'87 Oct.	Nov.	Dec.	'88 Jan.	Feb.
		RC12	RC02 RA01 RA12 RA11		RC11 RA12	RA14
Retorting, Gasifying, Oil & Heat Recovery	No. of Campaign					
	Operating	2 21	7 18 24	8 15 18	13 30	8 27
	Maintenance					
Drying	No. of Campaign		DC12, 13 DA06, 07	DA12, 11		DA14
	Operating		7 18 24	8		8 27
	Maintenance			15		
Fluidized Bed Combusting	No. of Campaign	FC11-PS FA01-PS	FC02-RS FA01-RS	FA11-PS FC11-RS	FC11'-RS RA11-RS	
	Operating	21 30	7 18	10 18	14 30	
	Maintenance		21	28		4

DISCUSSION ON PERFORMANCES OF RETORTING, GASIFYING AND OIL & HEAT RECOVERY PROCESSES

1. Independent Control of Retorting and Gasifying Processes

The shaft furnace is composed of two chambers, a retorting zone and a gasifying zone, which are connected with two connecting pipes.

Volume of gas leakage from the lower chamber to the upper chamber through the connecting pipe was maintained at about 2 % of

recirculating gas volume by controlling the extraction volume of by-product gas from the retort gas line. This gas leakage is detected and monitored as the pressure difference between top and bottom of the connecting pipes.

Success in suppressing the interference between the two processes to a negligible level was attributed to maintenance of a stable condition for each process.

It was confirmed that the control system using a basically constant controlled level of the gas supply condition to each zone was desirable for maintaining the stability of both retorting and gasifying processes as discussed below.

Table. 1 shows data of typical main test runs.

2. Retorting Performance

Size range of charged ore was 6-70 mm and the weighted average diameter was around 27 mm. Actual particle diameter in the furnace was smaller than the above figure due to the thermal shock of the retorting process, which is a well-known characteristic of both Condor and Maoming ores.

In result, the permeability resistance coefficient within the furnace was about 3 times of that of the cold state in the case of both Condor and Maoming ores. This value was almost equal to the experimental result obtained through 3 t/d bench scale plant operation.

The maximum gas space velocity which maintained stable permeability in such a shale-filled condition within the furnace was 0.6 - 0.7 Nm/sec.

The maximum ore processing amount restricted by the upper limit of supply hot gas volume was around 220 t/d (2000 kg/m²h) in both cases of Condor and pre-dried Maoming ores. As for Maoming ore, however, the above-mentioned figure was estimated based on the process data at the 160 t/d operation level (which was the maximum capacity due to restriction by the capacity of pre-drying equipment: 15-17 % → 4-5 %).

Table 1. Typical examples of main retorting test runs

1. Feed Ore		Condor	Maoming (Pre-dried)
Moisture Contents	wt %	8.4	5.0
2. Retorting Performances			
Feed Rate	t/d	220	160
Average Processing Rate	kg/m ² h	2,000	1,450
Recirculating Gas			
Volume	Nm ³ /h	10,100	6,850
Temperature	°C	590	590
Top Gas Discharged from Retorting Zone			
Temperature	°C	120	150
Pressure Loss of Retorting Zone	mm Aq	1,700	800
3. Oil Recovery			
Performances			
Oil Yield	l/t	58	78
Oil Recovery Rate	% of F/A	100	102
4. By-Product Gas Re- covery Performances			
Volume	Nm ³ /h	500	400
Lower Calorific Value	kcal/Nm ³	2,730	2,960
5. Gasifying			
Performances			
Volume	Nm ³ /h	8,710	6,400
Temperature	°C	230	230
Top Gas Discharged Gasifying Zone			
Temperature	°C	640	600
Composition			
H ₂	dry %	3.0	3.8
CO	dry %	3.6	4.5
Pressure Loss in Gasifying Zone	mm Aq	1,100	900
Gasification Rate	% of O.C.	76	74
6. Heat Recovery			
Performances			
Heat Recovery Rate			
No1. Recuperater	x10 ³ kcal/h	2,300	1,650
No2. Recuperater	x10 ³ kcal/h	900	700
Flue Gas Volume	Nm ³ /h	5,020	4,620
7. Shale Properties		FS RS SS	FS RS SS
T.C	wt %	10.5 5.3 1.4	13.8 7.4 2.1
H ₂	wt %	1.8 0.5 0.1	2.3 0.6 0.1
S ²	wt %	- 0.7 0.3	- 1.2 0.5

(FS: Feed shale, RS: Retorted shale, SS: Spent shale)

Oil recovery rate achieved about 100 % at the later stage of experiments (220 t/d for Condor and 160 t/d for Maoming). This was attributable to two improvements in equipment, aimed at the improvement of the uniformity. One was the increase of effective cross sectional area at the position of hot gas injection beams by narrowing the width of the beams, and the other was a decrease in shale size segregation in the furnace through improvement of the charging device.

3. Oil Recovery Performance

Most of the dust carried-over in top gas (about 4 g/Nm³) was collected efficiently (about 97 %) by a recovered-oil spray type cyclone and no dust troubles in the retort gas line were experienced. Heavy oil containing the dust was sent to a centrifugal separator. Solid contents at its outlet were less than 0.1% in recovered oil and more than 40% in sludge.

Two-stage tower coolers of multi-stage thin packed layer type were selected as the gas cooler taking into consideration cooling efficiency and prevention of dust clogging. Heavy oil is caught by the oil sprayed primary cooler and light oil and retort water are caught by the oil/water sprayed secondary cooler and EP. The suitability of this design concept was confirmed through operation. Carried-over oil mist at each cooling stage was 10-20 g/Nm³. Most of the oil mist was recovered by EP of the final stage to reach less than 1 g/Nm³ at its outlet.

4. Gasification Performance

Some shales begin to experience the cohesion phenomenon at temperatures above 1050 °C, which is a well-known characteristic of both Condor and Maoming ores.

Our concepts were to establish the process conditions which prevent the formation of hard cluster and to select a reliable device which maintains stability and uniformity in material flow even in the case of partial cluster formation.

The desirable temperature pattern in gasifying zone was governed by the supply gas volume and $O_2 + H_2O$ contents in supply gas. An appropriate amount of O_2 was supplied as an exothermic reaction agent and excess H_2O as a promotive agent for water gas reaction. 40-50 % of the heat generated in the gasifying zone was recovered as latent heat under the conditions which achieved the highest gasification rate. According to our experiences, this condition was the same as that for preventing the formation of hard cluster.

We presume that a small amount of weak cluster will normally be produced in our process. However, we believe that stable permeability has been maintained judging from the following:

- o High gasification rate of 70-80 %
- o Stable pressure loss in gasifying zone
- o Small O_2 leakage into the gas discharged from gasifying zone

These are attributed to the straight furnace configuration which has no reduced-sectional area portions and to the screw conveyors which have forced-discharging ability.

5. Heat Recovery Performance

The temperature of top gas discharged from the gasifying zone was normally $600^{\circ}C$ and $H_2 + CO$ contents in gas (dry base) were 8-10%. When the gas temperature after burning the combustibles in gas exceeded the design temperature at the inlet of recuperator (normally $850^{\circ}C$), the gas temperature was controlled by using a part of recirculating gas.

About 70 % of the heat recovered from the gasifying process was transferred to the recirculating retort gas through two recuperators which were installed in series. Remaining heat was transferred to the air through another recuperator and released into the atmosphere as hot air at $250^{\circ}C$.

Most of the carried-over dust (about 10 g/Nm^3) in the top gas was collected at an efficiency of about 90 % by normal cyclones. Very fine dust, however, stuck to the tube inside walls of shell & tube type recuperators and the heat exchange ability dropped below the

design value in one or two days operation. To overcome this problem, we installed a steel shot cleaning device. This device has been operating effectively since last August.

DISCUSSION ON FLUIDIZED-BED COMBUSTION PERFORMANCES

Throughout the preliminary and main test runs, satisfactory results were obtained. Typical operation data are shown in Table 2.

Table 2 Typical operation data

RUN NO.	FC-11(PS)	FC-02"(RS)	FA-11(PS)	FA-01(RS)
1.Feed Ore	Condor Powder Shale	Condor Retorted Shale	Maoming Powder Shale	Maoming Retorted Shale
2.Length of Run, h	62	63	54	65
3.Combustion Performances				
1)Feed Rate, t/h	2.91	6.3	2.61	4.5
2)Particle Size mm	3.5	2.4	2.9	2.6
3)Supply Air Vol.,Nm ³ /h	5,150	5,620	5,800	6,300
Temp, °C	169	392	97	276
Press. mmAq	450	615	400	570
4)Combustion Temp., °C	900 - 920	870 - 890	850 - 900	880 - 900
5)Combustion Efficiency, %	99 - 100	94 - 95	99 - 100	92
6)Dust Carry-over Ratio,%	24	8	44	15
4. Shale Cooler Performances				
1)Temp., °C	138	206	85	172
5. Shale Properties	[F.S] [S.S]	[F.S] [S.S]	[F.S] [S.S]	[F.S] [S.S]
1)OC, %	10.1 N.D	5.27 0.35	12.7 0.06	7.31 0.94
2)H, %	1.7 N.D	0.56 N.D	2.2 N.D	0.71 0.07
3)S, %	0.59 0.07	0.60 0.10	0.84 0.04	0.97 0.14
4)Calorific Value, kcal/kg.	1,170 -	520 -	1,440 -	700 -

(F.S: Feed shale, S.S: Spent shale)

The summary of results is as follows:

- 1) Combustion temperature of shale was around 900°C.
- 2) Moderate shale particle size ($D_p 50$) was 2 to 4 mm.
- 3) Combustion efficiency was better than 90%.
- 4) In the case of combustion of powdered shale, especially of Maoming, collapse phenomena were observed.
- 5) Combustion dust through dust cyclones, was very fine and sticky.
- 6) Sensible heat of spent shale was recovered at around 80 to 90% in a fluidized bed shale cooler.
- 7) Engineering data on scaling up were obtained for designing a commercial plant.

CONCLUSION

- 1) JOSECO constructed an oil shale pilot plant and commenced its operation early May 1987.
- 2) By minor modification of equipment and improvement of operation techniques, the oil shale pilot plant is currently operating efficiently and providing promising results.
- 3) JOSECO is confident of success in early establishment of its own technology.

ACKNOWLEDGMENTS

The work of Phase 2 has been 75% funded by MITI through JNOC and 25% by our share holding 35 companies.

JOSECO thanks China Petrochemical International Company, China and Southern Pacific Petroleum NL/Central Pacific Minerals NL, Australia for making available oil shale ores for the use of the pilot plant.